6. (Amended) The laminate according to Claim 1, wherein the sheet resistance value is from 0.5 to 3.5 Ω/\Box , the visible light transmittance is at least 40%, and the visible light reflectance is at most 10%.

- 7. (Amended) The laminate according to Claim 1, wherein a resin film having a low-reflecting property is further laminated thereon.
- 8. (Amended) The laminate according to Claim 1, wherein a resin film having an near-infrared shielding property is further laminated thereon.
- 9. (Amended) The laminate according to Claim 1, wherein the visible light reflectance is at most 3%.